



Product Data Sheet

FLEX INSIDE AND OUTSIDE PREFABRICATED CORNERS

PHYSICAL PROPERTIES

<u>Property</u>	<u>Test Procedure</u>	<u>Specification</u>
Color		White, Gray or Tan
Size	Inside Corner Outside Corner	2 3/4" Height x 2 3/4" Width x 2 3/4" Depth 2 3/4" Height x 5 1/2" Width x 2 1/2" Depth
Thickness	ASTM D-638	.070" Nominal
Specific Gravity	ASTM D-792	1.32g/cm ³
Tensile Strength	ASTM D-638	>2500 PSI
Elongation	ASTM D-638	>300%
Heat Aging	ASTM D-3045	90% of Original
Cold Resistance	ASTM D-1043	-400 F
Water Vapor Permeability	ASTM E-96	2.8g/m ² /day
Dimensional Stability	ASTM D-1240	0.5% or less
U.V. Stability	Xenon Arc 150	10,000 hrs. Excellent

APPLICATION

Hot air welded to Flex flashing and/or field membranes.