



# Product Data Sheet

## FLEX 140N GEOTEXTILE SEPARATION LAYER

### PRODUCT DESCRIPTION

Flex 140N Geotextile is a non woven geotextile composed of polypropylene fibers, which are formed into a stable network such that the fibers retain their relative position. Flex 140N Geotextile is inert to biological degradation and resists naturally encountered chemicals, alkalis, and acids.

The Flex 140N Geotextile is installed as a separation or protection layer in Flex Protected Membrane Roof Systems. It also is used as a protection layer and filtration fabric in Flex Garden Roof Systems and Flex Below Grade Waterproofing Systems. The Flex 140N has excellent physical and hydraulic properties in addition to high tensile strength. The Flex 140N provides the required strength and abrasion resistance to protect Flex Thermoplastic Roofing and Waterproofing Membranes withstanding installation and application stress to create an effective, long term solution.

### PHYSICAL PROPERTIES

<u>Property</u>	<u>Test Procedure</u>	<u>Specification</u>
Thickness	ASTM D 5199	.055ö
Weight	ASTM D 5261	4.8 oz/yd
Dimensions		15øx360ø
Tensile Strength	ASTM D 4632	120x120
Tensile Elongation	ASTM D 4632	50%
Tear Strength	ASTM D 4533	50lbs x 50lbs
Mullen Burst Strength	ASTM D 3786	225 psi
Puncture Strength	ASTM D 4833	70 lbs
Apparent Opening Size	ASTM D 4751	70 US Sieve
Permittivity	ASTM D 4491	1.8 sec <sup>-1</sup>
Permeability	ASTM D 4491	0.26 cm/sec
Flow Rate	ASTM D 4491	130 gal/min/ft <sup>2</sup>
UV Resistance (500 hrs)	ASTM D 4355	70%

**Disclaimer:** Flex Membrane International Corp. assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. Flex Disclaims any and all express, implied, or statutory standards, warranties or guaranties, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.