


ELASTOCOL[®] STICK ZERO

Zero VOC Polymer Based Primer



APPLICATIONS

ROOFING

WALLS

FOUNDATIONS

PRODUCT DATA SHEET PD10133 - REV 250804

PRODUCT NUMBERS:

- 37700 - 5 Gal (18.9 L) Pail

DESCRIPTION & FEATURES:

ELASTOCOL STICK ZERO is a zero VOC polymer based primer approved for use in roofing, walls and waterproofing assemblies. **ELASTOCOL STICK ZERO** is comprised of a proprietary blend of polymers, solvents and additives engineered to increase adhesion of self-adhered SBS membranes on approved substrates.

- Enhances the adhesion of self-adhesive membranes
- Resistant to water, alcohol and most saline, alkaline and diluted acids solutions
- Suitable for use on a variety of substrates, including gypsum, concrete, masonry, metal, wood and mineral-surfaced membranes

APPLICATION:



BRUSH



ROLLER

Thoroughly mix **ELASTOCOL STICK ZERO**, prior to application to the approved area via brush or roller.

Approximate coverage rates:

- Roofing:
Porous substrate - 517- 1,034 square feet per 5 gallons
Non-porous substrate - 827 - 2,069 square feet per 5 gallons
- Walls and foundations: 350 square feet per gallon

* Surface profile and porosity of the substrate will affect the coverage rates.

Ensure primer is tacky to-the-touch, but not wet before installing overlying membrane. Primer should not transfer to the fingertips when touched.

Refer to SOPREMA's published technical literature for additional details and application requirements.

STORAGE:

Store the container in an upright position to prevent damage. Store in a clean, dry location and cover as necessary to protect from environmental damage such as extreme cold, heat or moisture. **ELASTOCOL STICK ZERO** is a combustible material and should be kept away from open flames and other possible ignition sources during storage and use. Storage temperature range should be between 55°F (12.8°C) and 80°F (26.7°C).

LIMITATIONS

Adequate surface preparation is the key to proper adhesion. Ensure application surface is clean, dry and free of debris prior to application.

Ambient and surface temperatures must be between 14 - 100°F (-10 - 38°C). Do not attempt application if ice, snow, moisture or dew are present.

Primer should not be left exposed for extended periods or overnight to prevent contamination. If primer becomes fully dry, dirty and tack-free, re-prime the substrate as necessary to achieve membrane adhesion.

Do not accelerate drying of **ELASTOCOL STICK ZERO** by heating it with a torch.

TESTING & APPROVALS:



FLORIDA BUILDING CODE




NOA # 22-0706.01

WARRANTY:

For more information refer to www.SOPREMA.us or contact your SOPREMA representative.

ELASTOCOL[®] STICK ZERO

Zero VOC Polymer Based Primer



APPLICATIONS

ROOFING

WALLS

FOUNDATIONS

PRODUCT DATA SHEET PD10133 - REV 250804

TECHNICAL INFORMATION & TESTING:

| PHYSICAL PROPERTIES | | |
|--|--|------------------|
| PROPERTY | VALUE | ASTM TEST METHOD |
| Technology | Proprietary blend of synthetic polymers, solvents and resins | - |
| Color | Copper | - |
| Specific gravity at 68°F (20 °C), lb/gal (kg/L) | 7.8 (0.94) | D2240 |
| Flash point, °F (°C) | 14 (-10) | D92 (Closed cup) |
| Viscosity, Brookfield @ 77°F (25°C), cP | 300 - 600 | - |
| Solids by weight, % | 49 | D6511 |
| Application temperature, °F (°C) | 14 -100 (-10 - 38) | - |
| Storage temperature, °F (°C) | 55 - 80 (12.8- 26.7) | - |
| Drying time @ 72°F (50% RH), min | 30 - 90 | - |
| Cleanup | Mineral spirits | - |
| Shelf life, months | 60 | - |
| VOC content, g/L | 0 | D2369 |

* Data is represented by average values, unless noted otherwise.

SUSTAINABILITY



| |
|-------------------------------------|
| VOC CONTENT LOW EMITTING |
| 0 g/L |

Distributed By:

Flex[™]
Thermoplastic Single Ply and Multi-Ply
Roofing & Waterproofing Systems

5103A Pottsville Pike
Reading, PA 19605
Phone: 610-916-9500
Fax: 610-916-9501
www.FlexRoofingSystems.com

