



Product Data Sheet

FLEX 1120N GEOTEXTILE **SEPARATION LAYER**

PRODUCT DESCRIPTION

Flex 1120N Geotextile is a non woven geotextile composed of polypropylene fibers, which are formed into a stable network such that the fibers retain their relative position. Flex 1120N Geotextile is inert to biological degradation and resists naturally encountered chemicals, alkalis, and acids.

The Flex 1120N Geotextile is installed as a separation or protection layer in Flex Protected Membrane Roof Systems. It also is used as a protection layer and filtration fabric in Flex Garden Roof Systems and Flex Below Grade Waterproofing Systems. The Flex 1120N has excellent physical and hydraulic properties in addition to high tensile strength. The Flex 1120N provides the required strength and abrasion resistance to protect Flex Thermoplastic Roofing and Waterproofing Membranes withstanding installation and application stress to create an effective, long term solution.

PHYSICAL PROPERTIES

<u>Property</u>	<u>Test Procedure</u>	<u>Specification</u>
Thickness	ASTM D 5199	.098"
Weight	ASTM D 5261	11.8 oz/yd
Dimensions		15'x300'
Tensile Strength	ASTM D 4632	300lbs x 300lbs
Tensile Elongation	ASTM D 4632	50%
Tear Strength	ASTM D 4533	115lbs x 115lbs
Mullen Burst Strength	ASTM D 3786	585 psi
Puncture Strength	ASTM D 4833	170 lbs
Apparent Opening Size	ASTM D 4751	100 US Sieve
Permittivity	ASTM D 4491	0.8sec ⁻¹
Permeability	ASTM D 4491	0.26 cm/sec
Flow Rate	ASTM D 4491	65 gal/min/ft ²
UV Resistance (500 hrs)	ASTM D 4355	70%

Disclaimer: Flex Membrane International Corp. assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. Flex Disclaims any and all express, implied, or statutory standards, warranties or guaranties, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.